


### Amendments to the Claims

1-3. (Cancelled)

4. (Currently amended) A heat-radiation-preventive glass ~~characterized in that~~ which comprises a heat-radiation-preventive coating film formed from a coating layer of ~~said a~~ water-based heat-radiation-preventive coating material for glasses according to ~~Claim 1 is~~ , wherein 0.001 to 10% by weight of a silane coupling agent represented by the following general formula (I) is added to deionized water having a total anion content of 700 mgCaCO<sub>3</sub>/L or lower, applied onto one side of a glass substrate so that said heat- radiation-preventive coating film has visible light transparency of 90% or more, solar- radiation heat absorptivity of 0.01 to 11% and radiation heat absorptivity within the wavelength band of heat radiation at ordinary temperature of 0.01 to 20%,



---


where X is a group reactive or compatible with organic materials, R<sub>1</sub>, R<sub>2</sub>, and R<sub>3</sub> are, each independently, OH or a group capable of generating a silanol upon hydrolysis and they may be the same or different from each other.

5-6. (Cancelled)

7. (Currently amended) The heat-radiation-preventive glass according to Claim 4, ~~characterized in that~~ wherein the thickness of said heat-radiation-preventive coating film is 0.01 to 10μm.

8. (Currently amended) A method of producing a heat-radiation-preventive glass which comprises a coating step wherein a coating layer is formed by coating ~~said a~~ water-

based heat-radiation-preventive coating material for glasses according to Claim 1, wherein 0.001 to 10% by weight of a silane coupling agent represented by the following general formula (I) is added to deionized water having a total anion content of 700 mgCaCO<sub>3</sub>/L or lower, onto one side of a glass substrate and a desiccating step wherein a heat-radiation-preventive coating film is formed by desiccating said coating layer so that said heat-radiation-preventive coating film has visible light transparency of 90% or more, solar-radiation heat absorptivity of 0.01 to 11% and radiation heat absorptivity within the wavelength band of heat radiation at ordinary temperature of 0.01 to 20%.



where X is a group reactive or compatible with organic materials, R<sub>1</sub>, R<sub>2</sub>, and R<sub>3</sub> are, each independently, OH or a group capable of generating a silanol upon hydrolysis and they may be the same or different from each other.

9. (Cancelled)

10. (Previously presented) A method of preventing heat radiation from a glass which has absorbed solar-radiation heat, wherein a heat-radiation-preventive glass according to Claim 4 is disposed so that the glass substrate side faces the direction from which solar-radiation heat is irradiated whereby heat radiation from said heat-radiation-preventive coating film side is prevented.

11-20. (Cancelled)

21. (New) The heat-radiation-preventive glass according to Claim 4, wherein X in said general formula (I) is an amino group.

22. (New) The heat-radiation-preventive glass according to Claim 4, wherein the coating material further comprises 0.005 to 3.5% by weight of a cationic surfactant or a nonionic surfactant.

23. (New) The method of producing a heat-radiation-preventive glass according to Claim 8, wherein X in said general formula (I) is an amino group.

24. (New) The method of producing a heat-radiation-preventive glass according to Claim 8, wherein the coating material further comprises 0.005 to 3.5% by weight of a cationic surfactant or a nonionic surfactant.